

## Technical data sheet

### evguard<sup>®</sup> MPE

Special high performance multi-layer polyester insert for heavy impacts and printed laminated safety glass applications

#### ↓ ● Stability

Ball drop test	DIN EN 356	44.2.MPE(200)	P2A
		44.2.MPE(600)	P4A
Blackwater Testing	TAS 201-94 (Large Missile)	55.4.MPE(800)	<i>approved</i>
	TAS 203-94 @ ±120 psf (Cycling)	55.4.MPE(800)	<i>approved</i>
American National Standard Institute	ANSI Z97.1		<i>approved</i>
Sound reduction	DIN EN ISO 10140-2	44.2.MPE(200)	37 db

#### 🔧 Processing

Minimum temperature	105 °C (220 F)
Maximum temperature	140 °C (284 F)
Production process	Vacuum lamination

#### 📏 Dimensions & Packaging

Thickness	0.2 mm
	0.4 mm
	0.6 mm
Width	1,250 mm
Sheet length max.*	1,400 mm
Reel length	0.2 mm–480 m
	0.4 mm–240 m
	0.6 mm–120 m
Reel core	76 mm cardboard core
Packaging of reels	on a pallet
Packaging of sheets	1 stack (ca. 500 kg) on a pallet

\* evguard<sup>®</sup> MPE is available in reels and sheets

evguard® is a thermosetting, ethylene-vinyl acetate based, interlayer for manufacture of laminated safety, security & design glass. The stability and strength of the laminate can be significantly increased in combination with our MPE.

## ↔ Properties

Composition	PET copolyester, special formulation
Glass transition point	~110 °C
Colour	colourless transparent glossy
Density	≈ 1.2 g/cm <sup>3</sup>
Shrinkage	≤ 5 % (140 °C @ 10 minutes, depending on thickness)



## Storage recommendation

Temperature	< 30 °C (85 F)
Humidity	< 80 %
Shelf life	use by 12 months after date of production Opened rolls and stacks have to be protected against direct sunlight and dust.



**Folienwerk Wolfen GmbH** T +49 (0)3494 6979 0  
Guardianstraße 4 F +49 (0)3494 6979 37  
06766 Bitterfeld-Wolfen info@folienwerk-wolfen.de  
Germany www.folienwerk-wolfen.de



[www.evguard.de/en](http://www.evguard.de/en)

### Disclaimer

Our information about our products and processes is based on extensive research and our considerable experience in the field of applied engineering. We provide this information, which to the best of our knowledge is correct, orally and in writing. In doing so, we do not assume any liability other than the liability agreed upon in the respective individual contract, and we reserve the right to make technical modifications in the course of our product development. However, this shall not release user from its obligation to verify the suitability of our products and processes for its own use. Purchaser's specifications of intended use shall only be binding, if we, at the time of contract conclusion, have confirmed in writing that the delivered goods are suitable for the use intended by Purchaser. This shall also apply to the protection of third party industrial property rights and to applications and processes.